# Transolac Finish QD

**Product code:**
TO 3.33

A quick drying alkyd finish for rapid refurbishment of containers and maintenance of steel structures in a marine and industrial environment.

## Physical properties:

| | |
|---|---|
| Colour | Transocean Colourshades |
| Gloss / Appearance | Gloss |
| Volume Solids | Approx. 45 % |
| Specific gravity | Approx. 1.1 g/ml |
| VOC | Approx. 490 g/liter |
| Flashpoint | >30°C |

## Usage data:

| **Film thickness** | Dry film thickness per coat (µm) | Wet film thickness per coat (µm) | Theoretical spreading rate ($m^2/l$) |
|---|---|---|---|
| Range | 30 - 50 | 65 - 110 | 15 - 9 |
| Recommended | 40 | 90 | 11.2 |

| **Curing Times** | Substrate temperature | | | |
|---|---|---|---|---|
| | 10°C | 23°C | 30°C | |
| Touch dry | 2 Hours | 1 Hour | 30 Minutes | |
| Dry to handle | 6 Hours | 4 Hours | 2 Hours | |
| Full cure | | | | |

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product and should be considered as guidelines only.
The actual drying time may be shorter or longer, depending on film thickness, temperature, ventilation, humidity, preceding paint system etc.

**Recoating intervals - see application section**

| | Substrate temperature | | | | | | | |
|---|---|---|---|---|---|---|---|---|
| | 10°C | | 23°C | | 30°C | | | |
| Recoated with | Min. | Max. | Min. | Max. | Min. | Max. | Min. | Max. |
| Single pack products | 1 Day | Indefinite | 1 Day | Indefinite | 1 Day | Indefinite | | |
| 2-pack products | N/A | N/A | N/A | N/A | N/A | N/A | | |

Recoating information is for guidance only and varies with local climate and environmental conditions. For specific recommendations, consult your local Transocean representative.
Best intercoat adhesion is achieved when the subsequent coat is applied before the preceding coat has fully cured.
Extended recoating intervals apply only to ambient atmospheric exposure. After prolonged exposure, roughen the surface to ensure intercoat adhesion.

## Surface Preparation:

**Coated substrates**
All surfaces should be clean, dry and free from contamination. Surfaces should be treated in accordance with ISO 8504:2000.

Ensure compatibility of the coated substrates with the selected paint system. If the remaining part of the existing coating system needs to be sweep-blasted, fine abrasive shall be used to avoid damage to the coating system.

Contact your local Transocean office for more information.

**Quick drying recoat remarks**
At 10°C, the product can be recoated after 1 hour but not later than 6 hours as wrinkling may occur.

At 23°C, the product can be recoated after 1 hour but not later than 4 hours as wrinkling may occur.

At 30°C, the product can be recoated after 1 hour but not later than 2 hours as wrinkling may occur.

## Application:

**Mixing:**

**Conditions:**

The relative humidity should be <90% during application and curing, unless otherwise specified in the product documentation. The substrate temperature should be ≥5°C and ≥3°C above the dew point of the air. Air temperature and relative humidity should be measured at substrate.
Generally, the maximum recommended surface temperature is 40°C. Higher substrate temperatures are acceptable provided dryspray is avoided by proper spray application and extra thinning if required. In extreme cases it may be necessary to reduce film thickness in order to avoid sagging.

**Methods:**

| | | |
|---|---|---|
| **Guiding data Airless spray** | Pressure at nozzle | 130 - 160 bar |
| | | 0.38 - 0.53 mm (0.015 - 0.021 in.) |
| | Spray angle | 50 - 65 degrees |
| | Volume of thinner | 0 - 3% |
| **Guiding data Airspray** | Pressure | 3 - 5 bar |
| | Nozzle size | 1.4 - 1.8 mm |
| | Volume of thinner | 0 - 5% |
| **Brush / Roller** | Suitable for stripe coats and touch-up work only. Volume of thinner: 0 - 5%. | |
| **Thinner** | Transocean Standard Thinner 6.01<br>Avoid excessive thinning as it will result in lower sag resistance and slower cure. In addition it may cause solvent entrapment, possibly risking blistering, pinholing and/or other coating defects. | |
| **Cleaner** | Transocean Standard Thinner 6.01 | |

## Additional Product information:

### Storage and shelf life

Storage: Store the product in compliance with national regulations in a dry, cool, well-ventilated area, away from heat and ignition sources. Keep materials in tightly closed original containers until use. Securely re-seal partially used containers and store as recommended. (See Section 7 of the relevant SDS.)

Shelf life: The stated value is a minimum; refer to “Guidance to Transocean Coatings Product Datasheets” for details.
Shelflife: Months

### Health and safety

Observe the safety warnings on the container label. A Safety Data Sheet (SDS) is available upon request.Comply with all applicable national and local safety regulations.
For professional use only. Wear appropriate PPE (overalls, gloves, goggles, respiratory protection, etc.) to avoid skin and eye contact.
Spraying should be carried out under well-ventilated conditions. If the product is flammable (see label/SDS), keep away from sparks, open flames, and heat sources. No smoking in the work area.
Avoid inhaling vapors and particulates. Maintain airborne concentrations below Occupational Exposure Limits (OEL) through adequate natural ventilation during application and drying.
In enclosed areas with insufficient ventilation, use local exhaust ventilation. If this is not feasible, wear a suitable respirator. Users must be trained in its proper use and limitations.

### Disclaimer

The information in this Product Data Sheet is provided in good faith and based on our current knowledge. However, Transocean Coatings cannot control substrate quality, surface preparation, application conditions, or environmental factors that may affect product application and performance. Accordingly, we accept no liability for the performance of this product or for any loss, damage, or injury arising from its use, whether direct, indirect, or consequential. Should any conflict arise between translations, the English version of this Product Data Sheet is authoritative and binding.

This Data Sheet supersedes all previous versions and must be communicated to all users. Users must:
- Conduct their own trials to verify the product’s suitability for their specific application and intended purpose.
- Confirm compatibility with intended substrates and conditions, which are beyond our control.
- Implement appropriate quality control procedures during application.
- Verify suitability for circumstances not covered in this Data Sheet.

Transocean Coatings maintains a policy of continuous product development. Technical data may be revised as new information or experience becomes available. For further information, contact our Technical Department.

| | |
|---|---|
| MID Number | 333-1001 |
| Print Date | 20-11-2026 |